# MIG DHMb® Lining System

**Exterior and Interior Application** 

# MIG-ESP®

# Primer quartz-filled

### **Product Description**

**MIG-ESP Primer quartz-filled** is a ready-to-use, solvent-free, quartz-filled and alkali-resistant primer, especially for the **DHMb Lining System** (DHMb = Double Hybrid Membrane). It is suitable for outdoor and indoor use.

#### **Technical consulting service**

Phone: +49 (0) 5258 - 974 82 0 E-Mail: info@mig-mbh.de

#### **Application Area**

Suitable as a bonding agent for smooth, non-absorbent substrates.

Before the subsequent application of **MIG** plasters as well as before the use of mineral and pasty products, whose lack of pretreatment can lead to deflagration of the finish plasters.

**MIG-ESP Primer quartz-filled** does <u>not</u> prevent the discolouration or penetration of foreign substances in subsequently applied coatings.

# **Substrate Preparation**

The substrate must be clean, dry, solid and free of efflorescence, dust and loose parts or release agents (e.g. formwork oil).

Dirty or sandy surfaces must be cleaned entirely through washing, brushing or high-pressure cleaner depending on the substrate.

When cleaning with water, make sure that the substrates are sufficiently dry.

For critical substrates, carry out a tensile adhesion test.



# **Processing**

**MIG-ESP**\* **Primer quartz-filled** is ready to use. After thorough stirring, generously apply undiluted with a lambskin roller, a brush or a suitable spraying tool and allow to dry.

The object and ambient temperature should not be below + 5°C and not above + 35°C. Prior to application of subsequent coats, ensure that the primed surface is sufficiently dry.

The drying time is approx. 12 hours under normal conditions (+ 20°C/60 % relative air humidity). Lower temperatures and higher humidity extend the drying time.

#### **General Information**

Do not mix with other types of material. Cover adjacent components well or protect them against splashes.

Clean tools thoroughly with water after use. The containers must be completely emptied and sent for recycling.

Please consult us in case of doubt regarding processing, substrate or structural features. Otherwise, the provisions of the current standards apply.

_			_	
Tec	hni	ical	LD:	ata

Application	exterior and interior
Density	$1.45 \text{ g/cm}^3 \pm 0.10$
Bonding agent base	copolymer dispersion
pH Value	8.0 ± 1.0
Colour	white
Drying time	approx. 12 hours
Processing temperature	+ 5°C to + 35°C

#### Consumption

#### MIG-ESP® Primer quartz-filled is applied undiluted.

The coverage rate is approx.  $0.20-0.30 \, \text{L/m}^2$  depending on the porosity of the substrate and the chosen application method.

Exact quantities can be determined by creating test areas.

#### Storage

At least 12 months shelf life from date of sale if stored dry, frost-free and cool under proper conditions in original sealed containers.



Phone +49 (0) 5258 - 974 82 0 Fax +49 (0) 5258 - 974 82 29 Email info@mig-mbh.de Web www.mig-mbh.de





MIG-ESP® Primer quartz-filled

# **Technical Data Sheet**

Page 3 of 3

# **Packaging**

5 L (per bucket) x 60 buckets (per pallet) = 300 L 15 L (per bucket) x 24 buckets (per pallet) = 360 L 1,000 IBC

#### **Customs Tariff Number**

32099000

**MIG 262** 

# MIG DHMb® Lining System – Products

<u>Coatings</u> <u>Primers</u>

MIG-ESP® Interior MIG-ESP® Sealing Primer
MIG-ESP® Exterior MIG-ESP® Special Primer
MIG-ESP® Interior Anti-Microbial MIG-ESP® Primer quartz-filled

MIG-ESP® Rooflect MIG-ESP® PVC Primer

MIG-ESP® Primer for Wood (for indoor use only)

<u>Plasters</u> MIG-ESP® Bitumen Primer

MIG Therm M 65 <u>Sealing</u>

MIG Therm M 55 MIG Sealer MIG Thermalife® Ecoplaster

MIG-HRP Heat Resistant Protector

MIG-HRP 280 Bonding Agent

MIG Impreg. Agent for Natural Stone Facades

MIG Therm L 14

# Legal information

The information in this publication is based on our current technical knowledge and experience. Due to the abundance of possible influences during the processing and application of our products, they do not release the user from carrying out his own tests and trials and are only general guidelines. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from this. Any industrial property rights as well as existing laws and regulations must always be observed by the user on his own responsibility.

With the publication of this data sheet, all previous data sheets lose their validity.

