

MIG DHMb® Lining System

Exterior and Interior Application

MIG Sealer

Product Description

MIG Sealer is a ready-to-use, solvent-free sealer and was developed as an economical, fast-drying solution for numerous surfaces, especially for the **MIG-ESP® Interior** and **Exterior** products.

This allows surfaces to be sealed quickly and effectively without altering the material.

It is suitable for outdoor and indoor use.

Important: Under certain circumstances, a slight change in colour may occur.

Technical consulting service

Phone: +49 (0) 5258 - 974 82 0

E-Mail: info@mig-mbh.de

Application Area

One coat of **MIG Sealer** is recommended for most surfaces.

An additional layer may be required for extremely porous surfaces.

MIG Sealer is applied either with a soft brush, a roller or a spray bottle.

Substrate Preparation

The substrate must be clean, dry, solid and free of efflorescence, dust and loose parts or release agents (e.g. formwork oil).

Dirty or sandy surfaces must be cleaned entirely through washing, brushing or high-pressure cleaner depending on the substrate.

When cleaning with water, make sure that the substrates are sufficiently dry.

For critical substrates, carry out a tensile adhesion test.

Processing

MIG Sealer is ready to use. After thorough shaking, generously apply undiluted with a lambskin roller, a brush or a suitable spraying tool and allow to dry.

The object and ambient temperature should not be below + 5°C and not above + 35°C. Prior to application of subsequent coats, ensure that the primed surface is sufficiently dry.

The drying time is approx. 12 hours under normal conditions (+ 20°C/60 % relative air humidity). Lower temperatures and higher humidity extend the drying time.

General Information

Do not mix with other types of material. Cover adjacent components well or protect them against splashes.

Clean tools thoroughly with water after use. The containers must be completely emptied and sent for recycling.

Please consult us in case of doubt regarding processing, substrate or structural features. Otherwise, the provisions of the current standards apply.

Technical Data

Application	exterior and interior
Density	1.05 g/cm ³ ± 0.05
Bonding agent base	polymer based on: acrylic acid ester, methacrylic acid ester, styrene, resin-modified
pH Value	8.0 ± 1.0
Colour	yellowish white, dries colourless
Drying time	approx. 12 hours
Processing temperature	+ 5°C to + 35°C

Consumption

MIG Sealer is applied undiluted.

The coverage rate is approx. 0.15 – 0.30 L/m² depending on the porosity of the substrate and the chosen application method.

Exact quantities can be determined by creating test areas.

Storage

At least 12 months shelf life from date of sale if stored dry, frost-free and cool under proper conditions in original sealed containers.

Packaging

5 L (per canister) x 96 canisters (per pallet) = 480 L

10 L (per canister) x 60 canisters (per pallet) = 600 L

20 L (per canister) x 24 canisters (per pallet) = 480 L

1,000 L IBC

Customs Tariff Number

32099000

MIG DHMb® Lining System – Products

Coatings

MIG-ESP® Interior
 MIG-ESP® Exterior
 MIG-ESP® Interior Anti-Microbial
 MIG-ESP® Rooflect

Plasters

MIG 262
 MIG Therm M 65
 MIG Therm M 55
 MIG Thermalife® Ecoplaster
 MIG-HRP Heat Resistant Protector
 MIG-HRP 280 Bonding Agent
 MIG Therm L 14

Primers

MIG-ESP® Sealing Primer
 MIG-ESP® Special Primer
 MIG-ESP® Primer quartz-filled
 MIG-ESP® PVC Primer
 MIG-ESP® Primer for Wood (for indoor use only)
 MIG-ESP® Bitumen Primer

Sealing

MIG Sealer

Impregnation

MIG Impreg. Agent for Natural Stone Facades

Legal Information

The information in this publication is based on our current technical knowledge and experience. Due to the abundance of possible influences during the processing and application of our products, they do not release the user from carrying out his own tests and trials and are only general guidelines. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from this. Any industrial property rights as well as existing laws and regulations must always be observed by the user on his own responsibility.

With the publication of this data sheet, all previous data sheets lose their validity.